

Bitu-seal

1-K bitumen sealant

Features

- ▶ Optimal adhesion to bitumen, sheets, lead, copper and cement fibre boards
- ▶ Permanently elastic
- ▶ Weather and UV-resistant
- ▶ Fast skinning
- ▶ Quickly rainproof
- ▶ Resistant to ageing
- ▶ Temperature resistant
- ▶ Applicable with smoothing trowel and spreadable
- ▶ Silicone-free

Benefits of use

- ▶ Also for rain-slicked surfaces
- ▶ For normal caulking guns
- ▶ No heating necessary - can be processed cold
- ▶ High adhesion

Areas of application

- ▶ For grouting connections and penetrations in roofs, walls and floors
- ▶ For sealing and bonding leaks on roofing sheeting
- ▶ Safe performance "emergency repairs"



Bitu-seal

1-K bitumen sealant

Content 310 ml
Art.-No. 236 310EN

Content 6 kg
Art.-No. 236 006EN

Range of use

- ▶ Construction Industry
- ▶ Tinsmith craft
- ▶ Carpentry
- ▶ Structural-facings sector
- ▶ Ventilation construction
- ▶ Metal construction

Directions for use

The adhesion surfaces must be clean, stable and sound. **beko Bitu-seal** can be applied or spread with a smoothing trowel and can be smoothed with **beko smoothers**. When applied to wet surfaces, press on the material well and check the adhesion after drying. Perform your own tests before processing.

Caution

- ▶ Workable from +5° C (+41° F).
- ▶ Material is not paintable.
- ▶ Do not use in aquariums.
- ▶ Not suitable for marble and natural stone.
- ▶ Impurities can be removed with **beko Allclean**.
- ▶ In the case of incorrect or improper application, any product warranty becomes void.
- ▶ For professional and industrial use only.
- ▶ Please observe safety data sheet!

Accessories

	Art.-No.
Allclean Surface cleaner 500 ml	266 120 0500EN
Spatula, 30 mm	200 4 030



Technical data

Basis	Bitumen			
Processable	from +5° C (+41° F) up to +35° C (+95° F)			
Temperature	resistant from -35° C (-31° F) up to +110° C (+230° F) (in cured state)			
Freedom from adhesives	approx. 30 minutes (+23° C (+73.4° F) / 50% relative air humidity)			
Curing	approx. 1 mm/24 hours (+23° C (+73.4° F) / 50% relative air humidity) (dependent on temperature and layer thickness)			
Color	black			
Density	approx. 1,25 g/ml (1250 oz/ft ³)			
Viscosity	plasto-elastic			
Storage life	12 months (unopened), approx. 3 months once the package is opened			
Storage	at +5° C (+41° F) up to +25° C (+77° F); cool, frost-free and dry			
Contents/ packaging	Cartridge 310 ml Bucket 6 kg	25 pcs/box 2 pcs/box	1200 pcs/pallet 96 pcs/pallet	Art.-No. 236 310EN Art.-No. 236 006EN

Subject to technical changes.

Print date: May 2018.

This publication supersedes all previous editions and renders the latter invalid.