

# Quick & Easy Spray Multi-Primer

## Product description:

Water-based, quick-drying primer based on PU for low-overspray priming coats.

## Application:

Indoors and outdoors. For rational priming coats using the Quick & Easy spraying system. For application on wood, synthetic and metal surfaces with HVLP sprayers, such as the MEGA Quick & Easy 2.0/2.1.

## Properties:

- water-dilutable
- low-overspray and odourless
- excellent adhesion
- excellent edge coverage
- very good spreading rate
- insulates wood materials
- quick-drying
- very easy to sand
- suitable for children's toys according to DIN EN 71-3

## Binding agent:

Acrylic-based PU

## Spec. weight:

1.35 g/cm<sup>3</sup>

## Gloss level:

matte

## Shades of colour:

White and wide range of colours using the MEGA Mix paint mix service.

## Packaging size:

1.0 l and 2.5 l

## Application:

Spraying, stir well before use.

## Base surface preparation:

The surface must be free of dirt, separating substances and dry. Please observe VOB, Part C, DIN 18 363, sec. 3. Smoothed surfaces must be completely dry. Clean and sandpaper tightly adhering coats of paint well. Remove loose coats of paint. A test coat must be applied to a coil coatings, powder coatings and other critical surfaces. Adhesion must then be checked using a cross cut according to DIN EN 2409.

## Special information:

Prime content-rich woods with MEGA 057 Quick & Easy Spray wood blocking primer. When doing so, make sure the intermediate drying process suffices; best overnight.

## Technical specifications

### Dilution:

This product is ready for use (if necessary with water).

### Cleaning the tools:

Clean immediately after use using water.

### Consumption:

Approx. 100–150 ml/m<sup>2</sup>. Exact consumption data must be determined on the object.

### Drying process:

At 20°C and 50% rel. humidity.  
 dust dry: after approx. 1 h  
 dry to handle: after approx. 2 h  
 can be reworked: after approx. 6–8 h  
 (with synthetic resin paints after approx. 16 h)  
 Full hardening: after approx. 24 h

## Spraying data

### MEGA Quick & Easy 2.0/2.1:

Dilution: undiluted

### HVLP devices:

Nozzle: No. 3  
 Pressure: 0.5 bar

## General information

### Processing temperature:

Do not process below +5°C (ideal range 10 to 25°C). Pay attention to moistness with dew and object temperature. Low temperatures and/or high humidity prolong the drying process and lead to damage to the painted surface.

### Storage:

Can be stored in the sealed original container in dry, cool and frost-free conditions for at least 12 months.

### Composition according to VDL Guideline:

Acrylic/PU dispersion, titanium dioxide, zinc phosphate, talcum, water, additives, preservatives: 1,2-benzisothiazol-3(2H)-one

## Information on disposal:

For disposal, please observe the legal regulations. Waste code 080 112 (liquid), 170 701 (dry)

## Hazard warnings and safety instructions:

Harmful to aquatic organisms, with long-term effect. Keep out of the reach of children. Dispose of the content/container in accordance with local regulations. Contains: 1,2-benzisothiazol-3(2H)-one Can cause allergic reactions.

## EU threshold value for this product:

Product category: A/i  
 140 g/l VOC (2010)  
 This product contains a max. of 140 g/l VOC.

## GISCODE:

BSW30

## Observe the safety data sheet!

