

Ready to Use Paste

Product description:

MEGA 805 Ready to Use Paste is a ready-to-use, unfilled and solvent-free dispersion-based paste for indoor use.

Application:

To hang ingrain, textured, vinyl and paper wallpapers on dry, viable ceilings and walls.

Properties:

- ready to use
- plasticiser- and solvent-free
- ideal paste division
- excellent initial adhesion with good correctability
- is transparent when dry
- free of harmful emissions
- not suitable for damp/wet rooms

Binding agent basis:

PVAC reinforced starch derivative

Spec. weight:

approx. 1.0 kg/l

pH value:

8 - 9

Shade of colour:

Whitish/opaq. Transparent after drying

Packaging size:

15 l

Application:

Suitable for applications using a brush or pasting machine. MEGA 805 Ready to Use Paste is applied undiluted and evenly on the back of the wallpaper. The pasted length of wallpaper is then folded together 2/3 to 1/3. Observe the respective soaking time. Make sure the wallcovering is wrapped around at least 10 cm on the outer corners, to ensure a proper alignment of the following strips.

Observe the manufacturer's wallpapering instructions.

Please observe:

Immediately remove adhesive that may escape in the area of the seam by dabbing using a clean, damp cloth.

Surface:

The surface must be clean, dry, viable, evenly absorbent and smooth. The guidelines for base surface preparation as per the VOB, Part C, DIN 18 363 and 18 366 of the BFS Bulletin no. 16 must be observed.

Technical specifications
Cleaning the tools:

Clean immediately after use using water.

Drying process:

Surface dry and paintable at 20 °C and a rel. humidity of 50 % after approx. 8 - 12 hours. Open time amounts to approx. 20 minutes at normal room temperature.

Attention:

Paintable wallcoverings cannot be painted until they are completely dry.

Consumption:

approx. 150 - 300 ml/m² on smooth surfaces. Exact consumption data for the calculation must be determined on the object by means of a test coat.

General information
Storage:

Cool however, frost-free. Minimum shelf life if unopened is approx. 12 months.

Processing temperature:

At least +5 °C for air and surface during processing and drying. Do not use in the event of severe heat.

Declaration of the substances of content:

PVAC reinforced starch derivative, preservatives

Information on disposal:

Observe the legal regulations pertaining to disposal.

GISCODE:

D1

WHC1:

Self-classification

Observe the safety data sheet!

